

KURT HEIZMANN CERAMIC PARTS

Büsserachstrasse 28

CH - 4228 ERSCHWIL

CHEMICAL ANALYSIS STUMATIT

ELEMENT	%
Silicia SiO ₂	58
Alumina AL ₂ O ₃	29.7
Titanium TiO ₂	1.9
Iron Fe ₂ O ₃	1.4
Calcium CaO	0.5
Magnesium MgO	0.5
Potassium K ₂ O	0.8
Sodium Na ₂ O	0.3
LOI	6.7

THERMAL SHOCK - LOW VOLUME CHANGE ON FIRING !

www.keramikteile.ch